PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5 : G03G 9/12, 13/10

A1

(11) International Publication Number: WO 90/10894

(43) International Publication Date: 20 September 1990 (20.09.90)

(21) International Application Number: PCT/NL90/00025

(22) International Filing Date: 5 March 1990 (05.03.90)

(30) Priority data:
319,126 6 March 1989 (06.03.89) US

(71) Applicant: SPECTRUM SCIENCES B.V. [NL/NL]; Zijdeweg 6, NL-2244 BG Wassenaar (NL).

(72) Inventors: LANDA, Benzion ; 10010-119 Street, Edmonton, Alberta T5J 0J0 (CA). ALMOG, Yaacov ; 2 Hechalutz Street, 76 100 Rehovot (IL). PELED, Amnon ; 12 Jean Juares Street, 76 100 Rehovot (IL).

(74) Agents: DE BRUIJN, Leendert, C. et al.; Nederlandsch Octrooibureau, Scheveningseweg 82, P.O. Box 29720, NL-2502 LS The Hague (NL).

(81) Designated States: AT (European patent), BE (European patent), CA, CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), IT (European patent), JP, LU (European patent), NL (European patent), SE (European patent).

Published
With international search report.
With amended claims.

(54) Title: LIQUID DEVELOPER SYSTEMS WITH SELF-REPLENISHMENT OF BULK CONDUCTIVITY

(57) Abstract

A self-replenishing liquid developer system for an electrostatic imaging system including an insulating non-polar carrier liquid, toner particles dispersed in the carrier liquid, at least one charge director compound having a limited solubility in the carrier liquid and dissolved therein at its saturation concentration and excess of the at least one charge director compound comprised in a solid phase and being in equilibrium contact with the carrier liquid.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MR	Mauritania
BE	Belgium	GA	Gabon	MW	Malawi
BF	Burkina Fasso	GB	United Kingdom	NL	Netherlands
BG	Bulgaria	HU	Hungary	NO	Norway
BJ	Benin	IT	Italy	RO	Romania
BR	Brazil	JP	Japan	SD	Sudan
CA	Canada	KP	Democratic People's Republic of Korea	SE	Sweden
CF	Central African Republic			SN	Senegal
CG	Congo	KR	Republic of Korea	SU	Soviet Union
CH	Switzerland	LI	Liechtenstein	TD	Chad
CM	Cameroon	LK	Sri Lanka	TG	Togo
DE	Germany, Federal Republic of	LU	Luxembourg	US	United States of America
DK	Denmark	MC	Monaco		

LIQUID DEVELOPER SYSTEMS WITH SELF-REPLENISHMENT OF BULK CONDUCTIVITY

FIELD OF THE INVENTION

This invention relates to the field of electrostatic imaging, and more particularly to a liquid developer system having improved properties.

BACKGROUND OF THE INVENTION

In the art of electrostatic photocopying or photo printing, a latent electrostatic image is generally produced by first providing a photoconductive imaging surface with a uniform electrostatic charge, e.g. by exposing the imaging surface to a charge corona. The uniform electrostatic charge is then selectively discharged by exposing it to a modulated beam of light corresponding, e.g., to an optical image of an original to be copied, thereby forming an electrostatic charge pattern on the photoconductive imaging surface, i.e. a latent electrostatic image. Depending on the nature of the photoconductive surface, the latent image may have either a positive charge (e.g. on a selenium photoconductor) or a negative charge (e.g. on a cadmium sulfide photoconductor). The latent electrostatic image can then be developed by applying to it oppositely charged pigmented toner particles, which adhere to the undischarged "print" portions of the photoconductive surface to form a toner image which is sub sequently transferred by various techniques to a copy sheet (e.g. paper).

In liquid-developed electrostatic imaging, the toner particles are generally dispersed in an insulating non-polar liquid carrier, generally an aliphatic hydrocarbon fraction, which generally has a high-volume resistivity above 10^9 ohm cm, a dielectric constant below 3.0 and a low vapor pressure (less then 10 torr. at 25°C). The liquid developer system further comprises so-called charge directors, i.e. compounds capable of imparting to the toner particles an electrical charge of the desired polarity and uniform magnitude so that the particles may be electrophoretically deposited on the photoconductive surface to form a toner image. These charge director compounds are generally ionic or zwitterionic

compounds which are soluble in the non polar carrier liquid. This desired charging is achieved by providing a constant optimum concentration of charge director compound in the carrier liquid, which concentration is usually determined so as to achieve the highest copy quality for the particular application.

Stable electrical characteristics of the liquid developer, in particular its bulk conductivity, are crucial to achieve high quality imaging, particularly when a large number of impressions are to be produced without changing the liquid developer system. A major factor determining the electrical characteristics of the liquid developer and affecting the electrophoretic developing process of the toner particles, is the concentration of the charge director in the carrier liquid. Thus, one of the major problems arising in liquid-developed electrostatic imaging is the variation in the charge director concentration and it is believed that many low quality copies are a result of charge director imbalance in the liquid developer system.

The application of liquid developer to the photoconductive surface clearly depletes the overall amount of liquid developer in the reservoir of an electrocopying or electroprinting machine of this type. In practice, the liquid reservoir is continuously replenished, as necessary, by addition of two liquids from two separate sources, the one providing carrier liquid and the other - a concentrated dispersion of toner particles in the carrier liquid. This is necessary in order to maintain in the carrier liquid in the reservoir a relatively constant concentration of toner particles, because the total amounts of carrier liquid and toner particles utilised per electrocopy vary as a function of the proportional area of the printed portions of the latent image on the photoconductive surface. An original having a large proportion of printed area will cause a greater depletion of toner particles in the liquid developer reservoir, as compared to an original with a small proportion of printed area. Thus, in accordance with the aforementioned practice, the rate of replenishment of

carrier liquid is controlled by monitoring the overall amount or level of liquid developer in the reservoir, whereas the rate of replenishment of toner particles (in the form of a concentrated dispersion in carrier liquid) is controlled by monitoring the concentration of toner particles in the liquid developer in the reservoir. An optical float can combine both these functions, i.e. can be utilized to monitor both the overall amount of liquid developer in the reservoir and the toner particle concentration therein.

The amount of charge director in the liquid developer reservoir must also be replenished, since the charge director is also depleted together with the carrier liquid and the toner particles. In existing liquid-developed electrostatic imaging machines the charge director is replenished by adding it with the carrier liquid replenishment or with the concentrated toner dispersion. As explained hereinbelow, this results in charge director imbalance in the liquid developer system with consequent impairment of the quality of the copies.

As discussed above, the amount of toner particles utilized per electrocopy varies in proportion to the relative printed area of the image. Thus, a large number of so-called "white" copies (i.e. originals with small printed areas) will result in very small depletion of toner particles whereas the amount of carrier liquid depleted will be comparatively large. This amount of carrier liquid will be replenished and, in machines designed for adding the charge director only with the replenished carrier liquid, this will result in an increase of the concentration of charge director relative to the toner concentration. It can easily be seen that an opposite result will be observed in a photocopier machine designed so that the charge director is replenished together with the concentrated toner suspension only. In such machines a large number of "white" copies will cause a decrease in the concentration of charge director in the liquid developer system.

Similarly, a large number of "black" copies (i.e.

originals with large printed areas) will cause a degradation of copy quality in opposite directions to the above. In machines wherein charge director is added with the carrier liquid only, a large number of black copies will reduce the concentration of charge director in the liquid developer, resulting in degraded copies. Against this, in machines where charge director is added to the reservoir with the concentrated toner suspension only, its concentration in the liquid developer will be increased by a larger number of black copies, resulting in lighter than optimal copies.

A possible solution to the above problem of charge director imbalance in the liquid developer would be to monitor separately the concentration of the charge director and replenish it separately from a separate source. This solution, however, is uneconomic, because it would involve the cost and complexity of providing additional measurement devices and replenishment mechanism. It follows that a simpler and more feasible solution to the problem is needed.

It is an object of the present invention to provide a solution to the problem of charge director imbalance in liquid developer systems, thereby to maintain a constant high-quality of copies in electrostatic imaging processes, independent of the "print" proportions of the originals.

Other objects and advantages of the present invention will become clear from the following description of the invention.

SUMMARY OF THE INVENTION

The above object is achieved by the present invention which, in accordance with one aspect thereof, provides a self-replenishing liquid developer system for use in electrostatic imaging, which system comprises:

(a) an insulating non-polar carrier liquid;

(b) toner particles dispersed in said carrier liquid;

(c) at least one charge director compound having a limited solubility in said carrier liquid and dissolved therein at its saturation concentration; and

(c) excess of said at least one charge director compound comprised in a solid phase and being in equilibrium

contact with said carrier liquid.

The present invention is based on the concept of using a charge director compound which has a limited low solubility in the carrier liquid, such that the saturation concentration of the charge director in the carrier liquid is at a proper concentration as to bring about the electrical charging of the toner particles, to disperse them and to maintain them at the desired degree of dispersion. When such a saturated solution of charge director in the carrier liquid is maintained in contact with a solid phase comprising or consisting of a considerable excess of the charge director compound, this solid phase will serve as a reservoir for the charge director compound. Whenever the concentration of this charge director in the liquid phase, i.e. in the carrier liquid in contact with the solid phase, falls below its saturation concentration value, it will be rapidly equilibrated with the excess charge director in the solid phase so that the saturation concentration of the charge director in the carrier liquid is constantly and automatically maintained. As shown in the following, non-limiting examples, suitable charge director-carrier liquid-toner systems can be found which have the desired characteristics.

In accordance with one embodiment of the present invention, it is the toner particles themselves which serve as the solid phase comprising the excess charge director compound. To this end, from about 5 to about 10% by weight of charge director compound, based on the total weight of the imaging material, are milled together with the remaining ingredients of the imaging material to form the toner particles.

In accordance with this embodiment the concentration of the charge director compound is continuously maintained by natural and rapid equilibration between the charge director in solution in the carrier liquid and the excess charge director comprised in the toner particles. When, for example, a large number of white copies are made, resulting in a replenishment of pure carrier liquid thereby lowering

the concentration of charge director in the liquid developer, some charge director compound will diffuse from the solid phase, i.e. from within the toner particles, into the carrier liquid until dynamic equilibrium is reached when the concentration of charge director in the carrier liquid reaches its saturation value. In the opposite case, where a large number of "black" copies are made, consuming a relatively high proportion of toner particles as compared to the consumed carrier liquid, the resultant replenishment of concentrated suspension of toner particles in carrier liquid into the reservoir, would not affect the concentration of charge director because the added carrier liquid in said concentrated suspension will already be saturated with the charge director compound owing to the presence of excess of that compound in the toner particles in that concentrated suspension.

In accordance with an alternative embodiment of the present invention, the excess of charge director compound, preferably in the form of a finely dispersed powder, is contained in a container, at least a portion of the walls of which being made of a porous material which is permeable to the carrier liquid but does not permit the passage therethrough of the particulate solid charge director compound. Such container will be wholly or partially immersed in the reservoir of liquid developer so as to be in direct contact therewith. A suitable container may be, for example a closed bag made of thin porous sheet material, e.g. filter paper or the like. In this embodiment of the invention, the liquid developer is always in direct equilibrium contact with the excess charge director in solid form, thereby achieving a constant saturation concentration of charge director in the liquid developer.

The invention will be further described by the following, non-limiting examples, all of which relate to negative-working liquid developer systems, i.e. those in which the toner particles are negatively charged. It should be understood, however, that the invention is not limited to such negative-working liquid developers, but is rather

equally applicable to positive-working liquid developer systems. It should also be understood that the invention is not limited to the specific toner of Preparation 1 herein nor to the specific carrier liquids exemplified, but rather extends to all modifications falling within the scope of the claims.

PREPARATION I

Preparation of Black Imaging material

Black imaging material which is used in Examples 1 to 5 hereinbelow is prepared as follows:

10 parts by weight of Elvax 5720 (E.I. Du Pont), and 5 parts by weight of Isopar L (Exxon) are mixed at low speed in a jacketed double planetary mixer connected to an oil heating unit, for 1 hour, the heating unit being set at 130°C.

A mixture of 2.5 parts by weight of Mogul L carbon black (Cabot) and 5 parts by weight of Isopar L is then added to the mix in the double planetary mixer and the resultant mixture is further mixed for 1 hour at high speed. 20 parts by weight of Isopar L preheated to 110°C are added to the mixer and mixing is continued at high speed for 1 hour.

The heating unit is then disconnected and mixing is continued until the temperature of the mixture drops to 40°C.

EXAMPLE 1

Calcium laurylbenzenesulfonate in toner particles

Calcium laurylbenzenesulfonate was prepared from its 68 - 70% solution in xylol and isobutanol commercially available under the name Emcol P-1020 (Witco), by one of the following methods:

1) Emcol P-1020 is subjected to vacuum distillation at 170°C. The solid residue is allowed to equilibrate with air moisture and dissolved in Isopar H at the desired concentration.

2) The Emcol P-1020 is diluted with Isopar H to a 10% content of non volatile solids (n.v.s.) and the obtained solution is allowed to stand at room temperature whereupon a

yellow sediment is formed followed within 30 - 35 days by precipitation of a white material which is separated and dissolved in Isopar H at the desired concentration.

The crude material thus obtained is washed repeatedly with Isopar H with stirring until a constant conductance in the supernatant Isopar H solution is reached. The resultant solid residue was dried.

The solubility of calcium laurylbenzensulfonate in Isopar H was determined by U.V. spectrophotometry and found to be 0.069% by weight.

Preparation of the liquid developer.

One part by weight of the solid dry calcium lauryl benzenesulfonate was co-melted with 9 parts by weight of black imaging material at 130°C. The melt was cooled and 100 g thereof and 120 g of Isopar L were milled together for 19 hours in an attritor to obtain a dispersion of particles with an average diameter of about 2μ. The attrited material obtained was washed several times with Isopar H and then dispersed in Isopar H at a content of 1% n.v.s. The conductance of the toner was 3 pmho/cm.

The performance of the developer was tested in a Savin V-35 photocopier machine using both Savin 2200+ and Printers Stock copy sheets. The results obtained are summarised in the following Table 1.

TABLE 1

Substrate	Solid Area Density (SAD)	Fixing	Bleed through (SAD)
Savin 2200 +	1.51	good	0.15
Printers Stock	1.67	good	0.09

EXAMPLE 2

Sodium laurylbenzenesulfonate in toner

The title material was purchased from Fluka and used

without further treatment, after being left to equilibrate with air moisture. The material was repeatedly washed with Isopar H until a constant conductance of the supernatant solution was reached.

The solubility of sodium laurylbenzenesulfonate in Isopar H was determined spectrophotometrically to be 0.027% by weight.

__Preparation of the liquid developer__

One part of weight of sodium laurylbenzenesulfonate was co-melted with 9 parts by weight of black imaging material. 100 g of the co-melt were mixed with 120 g of Isopar G and attrited as described in Example 1 to give an average particle size of about 1.9μ. The final developer, after washing, had a conductance of 5.5 pmho/cm at a concentration of 1% n.v.s. in Isopar G. It was placed in the developer bath of a Savin 870 photocopier and the performance on various substrates was tested. The results are shown in the following Table 2.

__TABLE 2__

Substrate	S.A.D.	Transfer efficiency %
Gilbert Bond	1.33	72
Printers Stock	1.64	87

__EXAMPLE 3__

__Sodium diamyl sulfosuccinate in toner__

The title material is commercially available under the name Aerosol AY (Cyanamide). It was used without further treatment, except for equilibration with the air humidity and successive washing with Isopar H to constant conductance (about 1-2 pmho/cm).

__Preparation of the developer__

5 parts of sodium diamyl sulfosuccinate and one part of aluminium stearate were co-melted with 44 parts by weight of black imaging material in accordance with the procedure described in Example 1. 100 g of the co-melt were added to

120 g of Isopar H and milled for 19 hours as described in Example 1. The milled toner thus obtained was washed several times with Isopar and diluted with Isopar G to a 1% n.v.s. content of toner.

The obtained dispersion was placed in the developer bath of a Savin 870 photocopier and the performance tested on various substrates. The results are summarised in the following Table 3.

TABLE 3

Substrate	S.A.D.	Transfer Efficiency (%)
Savin 2200 +	1.32	84
Gilbert Bond	1.61	63

EXAMPLE 4

Calcium laurylbenzenesulfonate in filter paper bag.

The material obtained as described in Example 1 was placed in a bag prepared from folded Whatman MN filter paper, and the bag was immersed in a liquid developer and the conductance of the liquid developer measured. From time to time the bag was removed from the liquid developer which was centrifuged to remove the supernatant and the resultant toner particles were redispersed in pure Isopar H. Thereafter, the filter paper bag containing the charge director compound was re-installed and after several hours of stirring the conductivity of the liquid developer was measured again. To eliminate effects related to possible permeation of the charged toner particles through the filter paper, the conductance values obtained were compared with those of an identical control bag immersed in pure Isopar H.

It was found that the conductance of the liquid developer surrounding the bag reached a time-independent steady-state value of about 4 pmho/cm at a toner concentration of 1% n.v.s. The same conductance value was observed when the bag was removed from the toner suspension and immersed in pure isopar H.

Measurements in a test plating cell showed negative plating with the above described liquid developer system.

EXAMPLE 5

When the procedure of Example 4 was repeated with sodium laurylbenzenesulfonate (in Isopar H), calcium di-isobutyl sulfosuccinate (in Isopar G) and sodium diamyl sulfosuccinate (in Isopar H using a bag made from Whatman No. 2 filter paper), similar results as in Example 4 were obtained.

In all the above cases, a steady-state conductance was reached and significant charge transport followed by negative plating were observed in the test cell. In the case of calcium diisobutyl sulfosuccinate a markedly low conductance of 0.5-2 pmho/cm was measured (at toner concentration of 1% n.v.s.), but this did not affect the pronounced charge transport and the negative plating in the cell.

What is claimed:

1. A self-replenishing liquid developer system for an electrostatic imaging system comprising:

(a) an insulating non-polar carrier liquid;

(b) toner particles dispersed in said carrier liquid;

(c) at least one charge director compound having a limited solubility in said carrier liquid and dissolved therein at its saturation concentration; and

(d) excess of said at least one charge director compound comprised in a solid phase and being in equilibrium contact with said carrier liquid.

2. A liquid developer system according to claim 1 wherein said excess of charge director compound is comprised in said toner particles.

3. A liquid developer system according to claim 1 wherein said excess of charge director compound is in a finely dispersed solid form and is comprised in a container in contact with and permeable to said carrier liquid throughout at least a portion of the walls of the container.

4. A liquid developer system according to claim 3, wherein said container is a bag made of thin sheets of a porous material.

5. A liquid developer system according to claim 4, wherein said porous material is filter paper.

6. A liquid developer system according to claim 1, wherein said carrier liquid is a branched chain aliphatic hydrocarbon or a mixture of such hydrocarbons.

7. A liquid developer system according to claim 1 wherein said carrier liquid is an isoparaffinic hydrocarbon fraction having a boiling range above 155°C.

8. A liquid developer system according to claim 1, wherein

said charge director compound is ionic or zwitterionic.

9. A liquid developer system according to claim 8, wherein said charge director compound is a metal soap.

10. A liquid developer system according to claim 1, wherein said charge director compound is capable of imparting a negative charge to the toner particles suspended in the carrier liquid.

11. A liquid developer system according to claim 9, wherein said charge director compound is calcium lauryl-benzenesulfonate.

12. A liquid developer system according to claim 9, wherein said charge director compound is sodium lauryl-benzenesulfonate.

13. A liquid developer system according to claim 9, wherein said charge director compound is sodium diamyl sulfosuccinate.

14. An electrostatic imaging process comprising the steps of:

(a) forming a latent electrostatic image on a surface;

(b) applying to said surface electrically charged toner particles from a liquid developer system according to claim 1, thereby to form a toner image on said surface; and

(c) transferring the resulting toner image to a substrate.

15. An electrostatic imaging process comprising the steps of:

(a) electrostatically charging a photoconductive surface;

(b) exposing said photoconductive surface to an optical image thereby forming a latent electro static image on said photoconductive surface;

(c) applying to said photoconductive surface electrically charged toner particles from a liquid developer system according to claim 1, thereby to form a toner image on said photoconductive surface; and

(d) transferring the resulting toner image to a copy sheet substrate.

16. A method for developing a latent electrostatic image in a liquid-developed electrostatic imaging process, which comprises the use of a liquid developer system according to claim 1.

17. A liquid-developed electrocopying or electroprinting apparatus comprising a self replenishing liquid developing system according to claim 1.

AMENDED CLAIMS
[received by the International Bureau on 13 August 1990 (13.08.90); original claims 6-8, 10-17 amended, all other claims unchanged (3 pages)]

1. A self-replenishing liquid developer system for an electrostatic imaging system comprising:

(a) an insulating non-polar carrier liquid;

(b) toner particles dispersed in said carrier liquid;

(c) at least one charge director compound having a limited solubility in said carrier liquid and dissolved therein at its saturation concentration; and

(d) excess of said at least one charge director compound comprised in a solid phase and being in equilibrium contact with said carrier liquid.

2. A liquid developer system according to claim 1 wherein said excess of charge director compound is comprised in said toner particles.

3. A liquid developer system according to claim 1 wherein said excess of charge director compound is in a finely dispersed solid form and is comprised in a container in contact with and permeable to said carrier liquid throughout at least a portion of the walls of the container.

4. A liquid developer system according to claim 3, wherein said container is a bag made of thin sheets of a porous material.

5. A liquid developer system according to claim 4, wherein said porous material is filter paper.

6. A liquid developer system according to any of the preceding claims wherein said carrier liquid is a branched chain aliphatic hydrocarbon or a mixture of such hydrocarbons.

7. A liquid developer system according to any of the preceding claims wherein said carrier liquid is an isoparaffinic hydrocarbon fraction having a boiling range above 155°C.

8. A liquid developer system according to any of the preceding claims wherein said charge director compound is ionic or zwitterionic.

9. A liquid developer system according to claim 8, wherein said charge director compound is a metal soap.

10. A liquid developer system according to any of the preceding claims wherein said charge director compound is capable of imparting a negative charge to the toner particles suspended in the carrier liquid.

11. A liquid developer system according to any of the preceding claims wherein said charge director compound is calcium laurylbenzenesulfonate.

12. A liquid developer system according to any of the preceding claims wherein said charge director compound is sodium laurylbenzenesulfonate.

13. A liquid developer system according to any of the preceding claims wherein said charge director compound is sodium diamyl sulfosuccinate.

14. An electrostatic imaging process comprising the steps of:

(a) forming a latent electrostatic image on a surface;

(b) applying to said surface electrically charged toner particles from a liquid developer system according to any of the preceding claims to form a toner image on said surface; and

(c) transferring the resulting toner image to a substrate.

15. An electrostatic imaging process comprising the steps of:

(a) electrostatically charging a photoconductive surface;

(b) exposing said photoconductive surface to an optical image thereby forming a latent electro static image on said photoconductive surface;

(c) applying to said photoconductive surface electrically charged toner particles from a liquid developer system according to any of claims 1-13 to form a toner image on said photoconductive surface; and

(d) transferring the resulting toner image to a copy sheet substrate.

16. A method for developing a latent electrostatic image in a liquid-developed electrostatic imaging process, which comprises the use of a liquid developer system according to any of claims 1-13.

17. A liquid-developed electrocopying or electroprinting apparatus comprising a self replenishing liquid developing system according to any of claims 1-13.

INTERNATIONAL SEARCH REPORT

International Application No PCT/NL 90/00025

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all)[6]

According to International Patent Classification (IPC) or to both National Classification and IPC

IPC5: G 03 G 9/12, 13/10

II. FIELDS SEARCHED

Minimum Documentation Searched[7]

Classification System	Classification Symbols
IPC5	G 03 G

Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in Fields Searched[8]

III. DOCUMENTS CONSIDERED TO BE RELEVANT[9]

Category *	Citation of Document,[11] with indication, where appropriate, of the relevant passages[12]	Relevant to Claim No.[13]
X	WO, A1, 8705128 (SAVIN CORPORATION) 27 August 1987, see page 2, line 16 - line 19; page 2, line 26 - line 27; claims 1,8 --	14-17
A	EP, A2, 0247369 (E.I. DU PONT DE NEMOURS AND COMPANY) 2 December 1987, see claim 1 --	1-17
A	GB, A, 2194644 (RICOH COMPANY LTD) 9 March 1988, see figures 17-20; claims 1,26 --	1-17

* Special categories of cited documents:[10]

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance, the claimed invention cannot be considered novel or cannot be considered to involve an inventive step

"Y" document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

IV. CERTIFICATION

Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report
7th June 1990	26.06.90
International Searching Authority	**Signature of Authorized Officer**
EUROPEAN PATENT OFFICE	F.W. HECK

Form PCT/ISA/210 (second sheet) (January 1985)

International Application No. PCT/NL 90/00025

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category *	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No
A	US, A, 3669886 (GEORGE E. KOSEL) 13 June 1972, see column 7, line 27 - line 38; abstract --	1-13
A	US, A, 4003500 (EBERHARD SCHÖRNIG) 18 January 1977, see abstract; claim 1 --	1-5
A	US, A, 4193683 (FRED R. LANGNER) 18 March 1980, see abstract; figure 5 --	1-5
A	US, A, 4656966 (ROBERT A. GUISTINA) 14 April 1987, see column 3, line 1 - line 13; figure 1 --	1-13
A	US, A, 4785327 (BENZION LANDA ET AL) 15 November 1988, see column 3, line 40 - line 48; abstract --	1-5
P,A	US, A, 4812382 (DOUGLAS E. BUGNER ET AL) 14 March 1989, see table II --	11-12
P,A	US, A, 4869991 (JOSEPH DEGRAFT-JOHNSON ET AL) 26 September 1989, see claims 1,2 -- --------	13

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO.PCT/NL 90/00025

SA 35167

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on 07/05/90
The European Patent office is in no way liable for theseparticulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
WO-A1- 8705128	27/08/87	AU-D-	7083687	09/09/87
		EP-A-	0259448	16/03/88
		JP-T-	63502855	20/10/88
		US-A-	4860924	29/08/89
EP-A2- 0247369	02/12/87	JP-A-	62267767	20/11/87
		US-A-	4707429	17/11/87
		US-A-	4740444	26/04/88
GB-A- 2194644	09/03/88	DE-A-	3725002	04/02/88
		JP-A-	63033765	13/02/88
		US-A-	4860050	22/08/89
		JP-A-	63132273	04/06/88
		JP-A-	63085570	16/04/88
		JP-A-	63109478	14/05/88
		JP-A-	63109479	14/05/88
		JP-A-	63109480	14/05/88
US-A- 3669886	13/06/72	NONE		
US-A- 4003500	18/01/77	AT-B-	323557	10/07/75
		AU-B-	473228	17/06/76
		AU-D-	3738571	28/06/73
		BE-A-	777425	28/06/72
		CA-A-	961635	28/01/75
		CH-A-	532805	15/01/73
		DE-A-	2064709	27/07/72
		FR-A-	2121189	18/08/72
		GB-A-	1378523	27/12/74
		NL-A-	7117584	04/07/72
US-A- 4193683	18/03/80	NONE		
US-A- 4656966	14/04/87	NONE		
US-A- 4785327	15/11/88	EP-A-	0306174	08/03/89
		JP-A-	1140157	01/06/89
US-A- 4812382	14/03/89	NONE		
US-A- 4869991	26/09/89	AU-D-	3412989	16/10/89
		WO-A-	89/09432	05/10/89

For more details about this annex : see Official Journal of the European patent Office, No. 12/82